

8847 Fiberglass Hull Board

VBD Reinforced Foil Facing

Description

8847 Fiberglass Hull Board is composed of a lightweight, semirigid, incombustible fiberglass board with a durable silver fiberglass scrim Polyester facing system that can be painted. The felted nominal 2.9 lb. density fiberglass base board offers low organic content. The faced insulation board is used to meet thermal requirements and enhance acoustical stiffeners and duct work on pleasure craft, work boats, ferries, cruise ships, military vessels, and offshore platforms.

Specifications

* Approved as meeting Parts 2 and 5 of Annex 1 of the IMO FTP code by the U.S. Coast Guard per 164.112/144/0

Advantages

Thermal Insulation - This effective insulation system (R Value 4.34 per inch) minimizes heat transfer / energy loss providing a more comfortable, energy efficient environment.

Quality Control - Panels are produced in compliance with an established quality control program, under follow-up service with Intertek Testing Services NA Ltd., a qualified independent third party inspection agency. This ensures consistent, high quality finished materials.

Fluid Resistant - Facing system is resistant to oil and water. **Puncture Resistance** - Facing system offers improved puncture resistance.

Improved Acoustics - Aids with environment sound control.

Installation

8847 Fiberglass Hull Board is easy to cut and fit and installs with appropriate insulation pins, clips, and tape. It can also be fabricated into beam wraps and other structural component covers.

Availability

Standard Sizes:

8847 Fiberglass Hull Board is available through SPI service centers nationally. Call or visit our website to locate one near you.



Performance Compliance Data

Facing: Color Silver, composition, Foil / Scrim / Metalized Polyester, .009 inch thickness, .0188 lbs. / sf. **Base Board:** Coast Guard/IMO Approved 164.109/46/0, MIL-I-742F, Type II

Operating Temperature Limit: 450°F (232°C) **Nominal Density 2.9 pcf** (46.5 kg/m³)

Thermal Conductivity

ь л	- .	, TI 10 I I	TI 10 1 11 11			
Mean Temperature		e I nermai Conduct	Thermal Conductivity			
°F	°C	Btu•in/(hr•ft2•°F)	W/m•°C			
75	24	0.23	.033			
100	38	0.25	.036			
200	93	0.31	.045			

Sound Absorption Coefficients

Complies with MIL-I-22023D Requirements Mounting Type A (flat on the floor) [Formerly No. 4]

<u>Thickness</u>			<u>F</u>	reque	ency,	H <u>z</u>		
inches	mm	125	250	500	1000	2000	4000	NRC*
1	25	0.06	0.26	0.75	0.99	1.04	1.02	0.75
2	51	0.24	1.00	1.11	1.08	1.06	1.05	1.05
*Noise reduction coefficient.								

Base Board SCS Certified - Minimum 25% Recycled ContentNote: properties as reported by base board manufacturer





8847 Fiberglass (VBD Reinforced Foil) Hull Board Quote / Order Form

		DATE
COMPANY	CONTACT	PHONE
PROJECT NAME & LOCATION		DATE REQUIRED
SHIP TO LOCATION		P.O. NUMBER

8847 Fiberglass (VBD Reinforced Foil) Hull Board	Board Size (inches & Sq. Ft.)			
,	Thickness	Width	Length	SF
Accessories	Length	Size	Diam.	Quantity
Insulation Stick Pin				
Silver Navy Washers	N.A.			
Std. Lock Washers	N.A.			
Joint Tape	N.A.		Roll	

Note: Final quantities rounded to full carton or packaged quantities.





SPI Specialty Products & Insulation 2101 Rexford Road Suite 300E Charlotte, NC 28211 Phone: (855) 519-4044

Web: www.spi-co.com E-mail: fabteam@spi-co.com March 2019 - 8847 Fiberglass Hull Board



Disclaimer and Limitation of Warranty. The purchaser/user is advised to consult with the appropriate professionals and to read the manufacturer's product information to determine the adequacy or appropriateness of the product for the use intended. SPI makes no claim or representation regarding the use or applicability of the products. Further, SPI makes no warranty, expressed or implied, and disclaims all warranties including warranties of merchantability and fitness for a particular purpose.

For additional information visit http://:www.spi-co.com

Please ask your SPI Sales Representative about other fabrication products and services.